

Larrondo IrOIU (VIZCAYA) España
 P.O. Box 1.323/48080 Bilbao
 Tel. 34-(4) 4 71 13 00
 Fax 34-(4) 4 53 16 36

Management Systems
 Certified by
 LRQA
 ISO 9001 / SGI 6000360
 ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
 FOREST PARK - CLEOBURY MORTIMER
 NRKIDDERMINSTER-DY 149BD-ENGLAND

Trade Mark - Zeichen des Lieferwerkes
 Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
 Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		198084		Date - Datum - Fecha 25 - 06 - 2014			
Our order N° Werks - Nr N° de Referencia		546856		Heat Schmelze Colada		374462		Your order N° Bestell - Nr Pedido N°			
								OL6327			
Steel Grade Werkstoff Calidad				316-S-11 AV				According to Entsprechend Corresponde			
								BS 970:PART 3:1991.			
Shape and Size - Gegenstand Perfil y dimensión			Tolerance - Toleranz Tolerancia			Bundles Bunde Bultos		Bars Stäbe Barras		Weight Gewicht Peso	
HEXAGON 25,4 mm			h 11 /DIN 176			6		266		3731 Kg	
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-13a. ASTM A 479 / A 479M-13b. ASTM A 276-13a. ASME SA 479 / SA 479M-13 NACE MR-0175-2003/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Paraq.4.3/DGR 97/23/EG						Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC					
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico					
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA					
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min.	325	375	550	20					
		Max.									
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	429	520	631	39	42	71	197		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						18,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,022	0,39	1,78	0,033	0,021	17,20	2,04	11,05	0,45	0,0355	0,19
Visual and dimensional inspection Besichtigung und Ausmessung O.K. Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle O.K. Control de Radioactividad			Antimixing test Spektralk Verwechslungspr O.K. Antimezcla			Grain Size Korngröße Tamaño de grano		
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK										EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng. Works Inspector Der Werkssachverständige Inspector de fábrica	
F9410 3/8" Medium Pressure Bulkhead Connector 20K Body											