



Larrondo IrOIU (VIZCAYA) España
 P.O. Box 1.323/48080 Bilbao
 Tel. 34-(4) 4 71 13 00
 Fax 34-(4) 4 53 16 36

Management Systems
 Certified by
 LRQA
 ISO 9001 / SGI 6000360
 ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NRKIDDERMINSTER-DY 149BD-ENGLAND

Trade Mark - Zeichen des Lieferwerkes
 Anagrama del suministrador 
 Works Inspector Stamp - Werkssachverständiger
 Sello del Inspector 

Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		198084		Date - Datum - Fecha 25 - 06 - 2014					
Our order N° Werks - Nr N° de Referencia		546856		Heat Schmelze Colada		374462		Your order N° Bestell - Nr Pedido N°					
Steel Grade Werkstoff Calidad		316-S-11 AV		According to Entsprechend Corresponde		BS 970:PART 3:1991.							
Shape and Size - Gegenstand Perfil y dimensión		HEXAGON 25,4 mm		Tolerance - Toleranz Tolerancia		h 11 /DIN 176		Bundles Bunde Bultos	6	Bars Stäbe Barras	266	Weight Gewicht Peso	3731 Kg
Requirements - Anforderungen - Exigencias													
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-13a. ASTM A 479 / A 479M-13b. ASTM A 276-13a. ASME SA 479 / SA 479M-13 NACE MR-0175-2003/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Paraq.4.3/DGR 97/23/EG					Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC								
Melting process / Erschmelzungsart / Proceso de Fusión					Heat treatment / Wärmebehandlung / Tratamiento térmico								
E.A.F. / A.O.D.					1060C 4H/Std WATER/WASSER/AGUA								
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-													
Test results - Ergebnis der Prüfungen - Resultados de los ensayos													
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules				
RD. 10,00 mm.		Min.	325	375	550	20							
		Max.											
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	429	520	631	39	42	71	197				
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co		
Min.						18,50	2,00	11,00					
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70				
	0,022	0,39	1,78	0,033	0,021	17,20	2,04	11,05	0,45	0,0355	0,19		
Visual and dimensional inspection Besichtigung und Ausmessung O.K. Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle O.K. Control de Radioactividad			Antimixing test Spektroskop Verwechslungspr O.K. Antimezcla			Grain Size Korngröße Tamaño de grano				
Remarks - Bemerkungen - Observaciones													
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK					<div style="border: 2px solid red; padding: 5px; text-align: center;"> FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL </div>					EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng. Works Inspector Der Werkssachverständiger Inspector de fábrica			
F9573 7/8" JIC Swivel x Swivel Adaptor 10K													