


Larrondo LOIU (VIZCAYA) España
 P.O. Box 1.323/48080 Bilbao
 Tel. 34-(4) 4 71 13 00
 Fax. 34-(4) 4 53 16 37



ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
 Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
 Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		205952		Date - Datum - Fecha 29 - 09 - 2014						
Our order N° Werks - Nr N° de Referencia		540975		Heat Schmelze Colada		372805		Your order N° Bestell - Nr Pedido N°						
Steel Grade Werkstoff Calidad		316-S-11 AV		According to Entsprechend Corresponde		BS 970:PART 3:1991.								
Shape and Size - Gegenstand Perfil y dimensión		HEXAGON 18,03 mm		Tolerance - Toleranz Tolerancia		h 11 / DIN 176		Bundles Bunde Bultos						
						6		Bars Stäbe Barras						
								Weight Gewicht Peso						
								3241 Kg						
Requirements - Anforderungen - Exigencias														
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-14a. ASTM A 479 / A 479M-14. ASTM A 276-13a. ASME SA 479 / SA 479M-13 SAE AMS 5653H-12. NACE MR-0175-2003/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Paraq.4.3/DGR 97/23/EG					Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC									
Melting process / Erschmelzungsart / Proceso de Fusión					Heat treatment / Wärmebehandlung / Tratamiento térmico									
E.A.F. / A.O.D.					1060C 4H/Std WATER/WASSER/AGUA									
Solution annealed/Abgeschreckt/Hilf temple-Cold drawn/Gezogen/Estirado-														
Test results - Ergebnis der Prüfungen - Resultados de los ensayos														
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kernschlag / Resiliencia ISO V Jules					
RD. 10,00 mm.		Min. 315	425	600	15									
		Max												
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	566	624	679	36	39	69	207					
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co			
Min.						18,50	2,00	11,00						
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70					
	0,020	0,44	1,66	0,035	0,028	18,95	2,05	11,10	0,40	0,0240	0,17			
Visual and dimensional inspection Besichtigung und Ausmessung O.K. Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle O.K. Control de Radioactividad			Antimixing test Spektrosk Verwechslungspr O.K. Antimezcla			Grain Size Korngröße Tamaño de grano					
Remarks - Bemerkungen - Observaciones														
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK					<div style="border: 2px solid red; padding: 5px; color: red; font-weight: bold;"> FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL </div>					EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng. Works Inspector Der Werkssachverständige Inspector de fábrica				
F9684 1/4" BSP SWIV CAPS 10K 316L														