


Larrondo LOIU (VIZCAYA) España
 P.O. Box 1323/48080 Bilbao
 Tel. 34-(4) 4 71 13 00
 Fax 34-(4) 4 53 16 36



ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 149BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
 Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
 Sello del Inspector



Certificate type - APZ Nach Certificado tipo EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n° 197524		Date - Datum - Fech: 19 - 06 - 2014							
Our order N° Werks - Nr N° de Referencia 543321	Heat Schmelze Colada 374454	Your order N° Bestell - Nr Pedido N° OL6292									
Steel Grade Werkstoff 316-S-11 AV Calidad		According to Entsprechend BS 970:PART 3:1991. Corresponde									
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 27 mm	Tolerance - Toleranz Tolerancia h 11 / DIN 176	Bundles Bunde 2 Bultos	Bars Stäbe 72 Barras	Weight Gewicht Peso 1118 Kg							
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-13a. ASTM A 479 / A 479M-13b. ASTM A 276-13a. ASME SA 479 / SA 479M-13 NACE MR-0175-2003/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Paraq.4.3/DGR 97/23/EG			Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC								
Melting process / Erschmelzungsart / Proceso de Fusión E.A.F. / A.O.D.			Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA								
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estrado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas	Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschschlag / Resiliencia ISO V Jules			
RD. 10,00 mm.	Min. 325	375	550	20							
	Max.										
Temperature °C 20	Spec. N° Probe Nr. Pro N° 1	381	422	575	47	50	74	179			
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,023	0,55	1,75	0,031	0,027	17,00	2,02	11,10	0,42	0,0240	0,20
Visual and dimensional inspection Besichtigung und Ausmessung O.K. Control visual y dimensional	Radioactivity inspection Radioaktivitätskontrolle O.K. Control de Radioactividad	Antimixing test Spektrosk Verwechslungspr O.K. Antimezcla	Grain Size Korngröße Tamaño de grano								
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK						FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL			EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng.		
F9803 3/8" MEDIUM PRESSURE MALE X 1/2" BSPP MALE ADAPTOR 20K 316L						Works Inspector Der Werkssachverständiger Inspector de fábrica					