


Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax.34-(4) 4 53 16 36



ACEROS INOXIDABLES

**OLARRA**

**OLARRA U.K. LTD.**  
**FOREST PARK - CLEOBURY MORTIMER**  
**NR KIDDERMINSTER - DY14 9BD - ENGLAND**

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector



Certificate type - APZ Nach Certificado tipo <b>EN 10204/3.1</b>		Certificate n° - Prüf-Nr Certificado n° <b>200197</b>		Date - Datum - Fecha <b>11 - 07 - 2014</b>							
Our order N° Werks - Nr <b>546667</b> N° de Referencia		Heat Schmelze <b>376418</b> Colada		Your order N° Bestell - Nr <b>OL6322</b> Pedido N°							
Steel Grade Werkstoff <b>316-S-11 AV</b> Calidad			According to Entsprechend <b>BS 970:PART 3:1991.</b> Corresponde								
Shape and Size - Gegenstand Perfil y dimensión <b>HEXAGON 36 mm</b>		Tolerance - Toleranz Tolerancia <b>h 11 / DIN 176</b>		Bundles Bunde <b>6</b> Bultos	Bars Stäbe <b>130</b> Barras						
				Weight Gewicht <b>3577 Kg</b> Peso							
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-13a. ASTM A 479 / A 479M-13b. ASTM A 276-13a. ASME SA 479 / SA 479M-13 NAGE MR-0175-2003/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG			Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC								
Melting process / Erschmelzungsart / Proceso de Fusión <b>E.A.F. / A.O.D.</b>			Heat treatment / Wärmebehandlung / Tratamiento térmico <b>1060C 4H/Std WATER/WASSER/AGUA</b>								
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kernschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min. 325	375	550	20						
		Max.									
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	394	435	589	44	47	73	179		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,030	0,46	1,68	0,034	0,023	17,25	2,02	11,00	0,38	0,0205	0,17
Visual and dimensional inspection Besichtigung und Ausmessung <b>O.K.</b> Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle <b>O.K.</b> Control de Radioactividad			Antimixing test Spektroskop Verwechslungspr <b>O.K.</b> Antimezclia			Grain Size Korngröße Tamaño de grano		
Remarks - Bemerkungen - Observaciones										<b>EDV / EDP</b> <b>Acc. EN 10.204</b> <b>Alfredo Molina</b> <b>Certification</b> <b>Mng.</b>  Works Inspector Der Werkssachverständige Inspector de fábrica	
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK											
F9878 1" Medium Pressure x 3/4" BSPP Cone Seat Male x Male Adaptor 15K											