


Larrondo LOIU (VIZCAYA) España
 P.O. Box 1.323/48080 Bilbao
 Tel. 34-(4) 4 71 13 00
 Fax. 34-(4) 4 53 16 36



ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
 Anagrama del suministrador

Works Inspector Stamp - Werkssachverständiger
 Sello del Inspector

Certificate type - APZ Nach Certificado tipo EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n° 209776		Date - Datum - Fecha 27 - 10 - 2014							
Our order N° Werks - Nr 548607 N° de Referencia	Heat Schmelze 379800 Colada	Your order N° Bestell - Nr OL6406 Pedido N°									
Steel Grade Werkstoff 316-S-11 AV Calidad		According to Entsprechend BS 970:PART 3:1991. Corresponde									
Shape and Size - Gegenstand Perfil y dimensión HEXAGON 22,23 mm	Tolerance - Toleranz Tolerancia h 11 / DIN 176	Bundles Bunde 2 Bultos	Bars Stäbe 96 Barras	Weight Gewicht Peso 998 Kg							
Requirements - Anforderungen - Exigencias EN 10.088-3.2005. Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC EN 10.272-2007. ASTM A 182 / A 182M-14a. ASTM A 479 / A 479M-14. ASTM A 276-13a. ASME SA 479 / SA 479M-13 SAE AMS 5653H-12. NACE MR-0175-2003/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG											
Melting process / Erschmelzungsart / Proceso de Fusión E.A.F. / A.O.D.		Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA									
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estrado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas	Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules			
RD. 10,00 mm.	Min	325	375	550	20						
	Max										
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	466	621	685	32	35	72	229		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,023	0,36	1,77	0,034	0,028	17,15	2,03	11,00	0,36	0,0250	0,13
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional	O.K.		Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad	O.K.		Antimixing test Spektroskop Verwechslungspr Antimezcla	O.K.		Grain Size Korngröße Tamaño de grano		
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK						FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL			EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng. Works Inspector Der Werkssachverständige Inspector de fábrica		
F9956 1/4" NPT FEM X 3/8" NPT MALE HEX ADAPTOR 10K 316L											