


Larrondo LOIU (VIZCAYA) España
 P.O. Box 1.323/48080 Bilbao
 Tel. 34-(4) 4 71 13 00
 Fax.34-(4) 4 53 16 36



ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
 Anagrama del suministrador

Works Inspector Stamp - Werkssachverständiger
 Sello del Inspector

Certificate type - APZ Nach Certificado tipo EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n° 209776		Date - Datum - Fecha 27 - 10 - 2014							
Our order N° Werks - Nr 548607 N° de Referencia	Heat Schmelze 379800 Colada	Your order N° Bestell - Nr OL6406 Pedido N°									
Steel Grade Werkstoff 316-S-11 AV Calidad		According to Entsprechend BS 970:PART 3:1991. Corresponde									
Shape and Size - Gegenstand Perfil y dimensión HEXAGON 22,23 mm	Tolerance - Toleranz Tolerancia h 11 / DIN 176	Bundles Bunde 2 Bultos	Bars Stäbe 96 Barras	Weight Gewicht 998 Kg Peso							
Requirements - Anforderungen - Exigencias EN 10.088-3.2005. Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC EN 10.272-2007. ASTM A 182 / A 182M-14a. ASTM A 479 / A 479M-14. ASTM A 276-13a. ASME SA 479 / SA 479M-13 SAE AMS 5653H-12. NACE MR-0175-2003/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG											
Melting process / Erschmelzungsart / Proceso de Fusión E.A.F. / A.O.D.		Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA									
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas	Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules			
RD. 10,00 mm.	Min	325	375	550	20						
	Max										
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	466	621	685	32	35	72	229		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,023	0,36	1,77	0,034	0,028	17,15	2,03	11,00	0,36	0,0250	0,13
Visual and dimensional inspection Besichtigung und Ausmessung O.K. Control visual y dimensional		Radioactivity inspection Radioaktivitätskontrolle O.K. Control de Radioactividad		Antimixing test Spektroskop Verwechslungspr O.K. Antimezcla		Grain Size Korngröße Tamaño de grano					
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK						FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL			EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng.		
F9960 1/4" BSPP HEX FULL SOCKET 10K 316L						Works Inspector Der Werkssachverständige Inspector de fábrica					