

Larrondo LOIU (VIZCÁYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax.34-(4) 4 53 16 36

Management Systems  
Certified by  
LRQA  
ISO 9001 / SGI 6000360  
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

**OLARRA**

**OLARRA U.K. LTD.**  
**FOREST PARK - CLEOBURY MORTIMER**  
**NR KIDDERMINSTER - DY 149BD - ENGLAND**

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate nº - Prüf-Nr Certificado nº		193253		Date - Datum - Fecha 21 - 05 - 2014					
Our order Nº Werks - Nr Nº de Referencia		542651		Heat Schmelze Colada		372805		Your order Nº Bestell - Nr Pedido Nº					
Steel Grade Werkstoff Calidad		316-S-11 AV		According to Entsprechend Corresponde		BS 970:PART 3:1991.							
Shape and Size - Gegenstand Perfil y dimensión		HEXAGON 28,58 mm		Tolerance - Toleranz Tolerancia		h 11 /DIN 176		Bundles Bunde Bultos	6	Bars Stäbe Barras	200	Weight Gewicht Peso	3442 Kg
Requirements - Anforderungen - Exigencias													
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-13a. ASTM A 479 / A 479M-13b. ASTM A 276-13a. ASME SA 479 / SA 479M-13 NACE MR-0175-2003/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG					Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC								
Melting process / Erschmelzungsart / Proceso de Fusión					Heat treatment / Wärmebehandlung / Tratamiento térmico								
E.A.F. / A.O.D.					1060C 4H/Std WATER/WASSER/AGUA								
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-													
Test results - Ergebnis der Prüfungen - Resultados de los ensayos													
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules				
RD. 10,00 mm.		Min.	325	375	550	20							
		Max.											
Temperature °C 20	Spec. Nº. Probe Nr. Pro Nº.	1	397	442	588	43	46	72	179				
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co		
Min.						18,50	2,00	11,00					
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70				
	0,020	0,44	1,66	0,035	0,028	16,95	2,05	11,10	0,40	0,0240	0,17		
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektrosk Verwechslungspr Antimezcla			Grain Size Korngröße Tamaño de grano				
O.K.			O.K.			O.K.							
Remarks - Bemerkungen - Observaciones													
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK													
F9970 1 1/16" JIC x 1/2" NPT Male x Male Adaptor 10K													
<div style="border: 2px solid red; padding: 5px; display: inline-block;"> <p style="text-align: center; margin: 0;">FLOW TECHNOLOGY LTD  TEST CERTIFICATE  VERIFIED TRUE  COPY OF ORIGINAL</p> </div>													
EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng.  Works Inspector Der Werkssachverständige Inspector de fábrica													